





INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6:

(11) International Publication Number:

WO 98/57887

C01B 21/28, B01J 8/02

(43) International Publication Date:

23 December 1998 (23.12.98)

(21) International Application Number:

PCT/GB98/01649

A1

(22) International Filing Date:

4 June 1998 (04.06.98)

(30) Priority Data:

9712444.0

17 June 1997 (17.06.97)

iB | ____

(71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB).

(72) Inventor; and

(75) Inventor/Applicant (for US only): SHIPLEY, David, Graham [GB/GB]; 12 Fir Tree Close, Hilton, Yarm, Cleveland TS15 9JZ (GB).

(74) Agents: GRATWICK, Christopher et al.; ICI Group Intellectual Property, P.O. Box 90, Wilton, Cleveland TS90 8JE (GB).

(81) Designated States: AU, BR, CA, CN, CZ, GE, HU, ID, JP, KR, MX, NO, NZ, PL, RO, SK, UA, US, UZ, Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).


Published

With international search report.

(54) Title: AMMONIA OXIDATION

(57) Abstract

In order to render the catalyst temperature more uniform in a catatylic ammonia oxidation process, the preheated reactants mixture, i.e. ammonia and oxygen—containing gas, is passed through a perforate reflector disposed upstream of the catalyst bed, said reflector being effective to reflect heat radiated from the inlet face of the catalyst bed back towards the catalyst bed.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	- GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada .	IT	Italy	MX	Mexico	UZ.	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	zw	Zimbabwe
CI	Côte d'Ivoire	KP	- Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation	••	
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

Ammonia oxidation.

10

15

20

30

35

This invention relates to ammonia oxidation. Ammonia oxidation is widely employed in the manufacture of nitric acid and hydrogen cyanide. In the manufacture of nitric acid ammonia is oxidised with air to nitric oxide, while in the manufacture of hydrogen cyanide a mixture of ammonia and methane (often as natural gas) is oxidised with air. In both processes, the gas mixture is passed at an elevated temperature over a catalyst to effect the oxidation. Side reactions, such as the formation of nitrogen or nitrous oxide, are undesirable. Consequently, in addition to good activity, the catalyst is required to have a good selectivity.

The oxidation reaction is exothermic: as the heated gas mixture passes through the catalyst, the oxidation reaction proceeds with the evolution of heat, causing the temperature of both the gas mixture and the catalyst to increase until a steady state condition is reached. The selectivity of the reaction depends on the catalyst temperature, and for any given operating conditions, i.e. gas composition, catalyst, catalyst age, flow rate etc. there is generally an optimum temperature. The catalyst temperature may be controlled by modification of one or more of the process variables, for example the temperature to which the gas mixture is pre-heated and/or the proportion of ammonia in the gas mixture.

We have noticed however that there is liable to be a significant temperature gradient through the catalyst and so not all the catalyst is operating at the desired optimum. In part this temperature gradient results from radiation of heat from the inlet side of the catalyst into the incoming gas mixture.

In the present invention the effect of such radiation is minimised.

Accordingly the present invention provides for the oxidation of ammonia comprising passing a mixture of ammonia and an oxygen containing gas preheated to an elevated temperature through at least one bed of a catalyst effective for the oxidation of ammonia wherein, in order to render the catalyst temperature more uniform, the gas mixture is passed through a perforate reflector disposed upstream of the catalyst bed, said reflector being effective to reflect heat radiated from the inlet face of the catalyst bed back towards the catalyst bed.

The catalyst may be platinum, optionally alloyed with other precious metals such as rhodium, in the form of meshes or gauzes formed from the metal wire. Alternatively the catalyst may be in the form of pellets, extrudates or granules of an oxidic material such as a composition containing cobalt oxide. For example, it has been proposed in CN-A-86 108 985 to employ lanthana/ceria/cobalt oxide compositions of the general formula La_{1-x}Ce_xCoO₃ (where x is from 0 to 1) made by a specified co-precipitation route as ammonia oxidation catalysts. Oxidic catalysts preferably contain at least one mixed oxide phase containing cobalt and at least one element A selected from rare earths and yttrium, said cobalt and element A being in such proportions that the element A to cobalt atomic ratio is in the range 0.8 to 1.2, particularly 1.0 to 1.2. Preferably at least

20

30

2

one element selected from yttrium, cerium, lanthanum, neodymium, and praseodymium is used as part or all of element A. Element A may comprise a mixture of at least one variable valency element Vv selected from cerium and praseodymium and at least one non-variable valency element Vn selected from yttrium and the non-variable valency rare earth elements such as lanthanum or neodymium. In particular it is preferred that the atomic proportions of variable valency element Vv to non-variable valency element Vn is in the range 0 to 1, particularly 0 to 0.3. Such oxidic catalysts may be in a form wherein the amount of oxygen is non-stoichiometric. This arises from the variable valency of cobalt and also of any variable valency rare earth present as part, or all, of element A.

In the process of the invention, a radiation reflector is disposed upstream of the catalyst to reflect heat radiated from the inlet face of the catalyst back to the catalyst. In this way heat loss from the inlet face of the catalyst is minimised and so the catalyst temperature is more uniform. The reflector is preferably a perforate plate disposed just upstream of the catalyst. The perforations should be of sufficient number and size that the reflector presents only an insignificant impedance to the flow of the gas mixture therethrough, but, on the other hand they should only form a minor proportion of the area of the reflector so that a substantial amount of the radiation is reflected. Preferably the perforations are in the form of louvres so that essentially all the area of the reflector acts to reflect the radiated heat. The reflector may also act as a diffuser to ensure even distribution of the gas mixture through the catalyst bed. The reflector is preferably positioned between 1 and 30 cm above the top of the catalyst bed.

The invention is illustrated by reference to the accompanying drawings wherein Figure 1 is a diagrammatic cross section of an ammonia oxidation reactor. Figure 2 shows an alternative arrangement.

In Figure 1 there is shown a vessel 1 having an inlet port 2 and an outlet port 3. Disposed across the vessel are catalyst beds 4, 5 each composed of a wad of gauzes formed from a platinum/rhodium alloy wire. Upstream of the bed 4 nearest the inlet port is disposed a reflector plate 6 formed from a suitable heat resistant metal such as Incalloy. A plurality of louvres 7 are provided in the reflector plate 6.

In use a mixture of ammonia and air, preheated to a desired inlet temperature, is fed to the inlet port 2. The mixture passes through louvres 7 in the reflector plate and then through the catalyst beds 4 and 5. Oxidation of the ammonia occurs with the evolution of heat. As a result the temperature of the both the catalyst and the gas mixture increases. The reacted gas then leaves the reactor via outlet port 3. Under steady state operation the temperature of the catalyst bed 5 and the reacted gas are essentially the same. Likewise the temperature through most of the thickness of the catalyst bed 4 is the same as that of the reacted gas mixture. However heat is liable to be lost from the inlet, i.e. upper, face of catalyst bed 4 by radiation into the incoming gas stream. A substantial amount of this radiated heat is reflected back towards the catalyst bed 4 by the reflector

15




plate 6, thereby reducing the temperature difference between the inlet portion of the catalyst bed 4 and the remainder of the catalyst bed. In this was the temperature of the catalyst bed is more uniform enabling the reaction conditions to be selected to give the optimum selectivity.

An alternative arrangement is shown in Figure 2. Here the reflector consists of a pair of metal plates 8, 9 spaced one above the other. Each plate is perforate so as to allow passage of the reactants through the plates, but the perforations are staggered so that heat radiated from the catalyst bed passing through the perforations of the lower plate is reflected by the lower surface of the upper plate.

In some cases it may be desirable to provide a layer of thermal insulation on the upper surface of the reflector, i.e. on the surface remote from the catalyst bed, to minimise heat loss from the upper surface of the reflector.

In the oxidation of ammonia to nitric oxide for the manufacture of nitric acid, the oxidation process may be operated at temperatures of 800-1000°C, particularly 850-950°C, pressures of 1 to 15 bar abs., with ammonia in air concentrations of 5-15%, often about 10%, by volume.

The selectivity tends to increase as the space velocity is increased, and so high space velocities, greater than 1.5 x 10⁵ h⁻¹, are desirable. The space velocity depends on the linear velocity of the feed gas (at NTP) and the depth of the catalyst bed. Linear gas velocities conventionally employed in commercial atmospheric pressure ammonia oxidation processes are usually in an excess of 2000 m/h, and typically are in the range 2500-8000 m/h, preferably 4000-6000 m/h. Commercial processes operating at elevated pressures tend to employ considerably higher linear gas velocities, for example 30000-40000 m/h. For economic reasons it is desirable for the bed depth to be less than 50 mm. For example with a bed of depth 20 mm, at a linear gas velocity of 4000 m/h, the space velocity is 2 x 10⁵ h⁻¹.

Claims

- A process for the oxidation of ammonia comprising passing a mixture of ammonia and an oxygen containing gas preheated to an elevated temperature through at least one bed of a catalyst effective for the oxidation of ammonia wherein, in order to render the catalyst temperature more uniform, the gas mixture is passed through a perforate reflector disposed upstream of the catalyst bed, said reflector being effective to reflect heat radiated from the inlet face of the catalyst bed back towards the catalyst bed.
- 2 A process according to claim 1 wherein the perforations in the reflector plate comprise louvres.
- 3 A process according to claim 1 wherein the reflector comprises a pair of perforate plates having their perforations staggered with respect to one another.
- 4 A process according to any of claims 1 to 3 wherein the reflector is provided with a layer of thermal insulation on the surface thereof remote from the catalyst bed.





Fig.2.



A. CL	ASSIFIC	ATION OF SUB	JECT MATTER
IPC	6	C01B21/28	B01J8/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols) IPC 6 C01B B01J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS	CONSIDERED	TO BE	RELEVANT

Category °	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	B. ELVERS ET AL.: "Ulmann's Encyclopedia of industrial chemistry; vol A17, 5th Ed." 1991 , VCH , WEINHEIM (DE) XP002077606 see page 307 - page 310; figures 15,17,18	1
X	US 3 462 243 A (RIGA JEAN JOSEPH) 19 August 1969 see column 3, line 49 - line 59	1
X	DE 37 31 988 A (STEINMUELLER GMBH L & C) 6 April 1989 see the whole document	1
A	US 4 170 455 A (HENRIE JAMES 0) 9 October 1979 see column 5, line 52 - line 58; figure 1 -/	1

X Further documents are listed in the continuation of box C.	X Patent family members are listed in annex.
Special categories of cited documents: A document defining the general state of the art which is not considered to be of particular relevance E earlier document but published on or after the international filling date L document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) O document referring to an oral disclosure, use, exhibition or other means P document published prior to the International filling date but later than the priority date claimed	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention." "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone. "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family
Date of the actual completion of the International search 16 September 1998	Date of mailing of the International search report 28/09/1998
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentiaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo ni, Fax: (+31-70) 440-3016	Authorized officer Zalm, W

1



In. .ti pileation No PCT/GB 98/01649

	DOCUMENTS CONSIDERED TO BE RELEVANT	
ategory C	tation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
	EP 0 275 681 A (JOHNSON MATTHEY PLC) 27 July 1988	
		·
Ē		
	•	

1

INTERNATIONAL SEARCH REPORT

mation on patent family members

In. at plication No PCT/GB 98/01649

Patent document cited in search repo	rt	Publication date	Patent family member(s)	Publication date
US 3462243	A	19-08-1969	NONE	
DE 3731988	Α	06-04-1989	NONE	·
US 4170455	Α	09-10-1979	CA 1084298 A JP 1270401 C JP 52134798 A	26-08-1980 25-06-1985 11-11-1977
EP 0275681	Α	27-07-1988	JP 59048339 B AU 603630 B	26-11-1984 22-11-1990
			AU 8267587 A CA 1304067 A DE 3781880 A	23-06-1988 23-06-1992 29-10-1992
			DK 679187 A FI 875549 A	24-06-1988
			GR 3005771 T JP 63233005 A MX 168762 B	07-06-1993 28-09-1988 07-06-1993
			US 4869891 A	26-09-1989